



## BOSS<sup>®</sup> 125 Multi~Seal Building/Construction Sealant

### TYPICAL PROPERTIES

#### Uncured

Flow Sag or Slump .....	NIL
Skin-Over Time, min. ....	5
Extrusion Rate g/min. ....	500


#### Cured – Physical

7 Days at 77°F (25°C) and 50% RH (1/8" thickness)

Hardness, Shore A .....	25
Specific Gravity .....	1.36
Tensile Strength, psi .....	350
Elongation, % .....	565
Modulus, psi .....	115
Shrinkage .....	NIL
Application Temperature Range .....	-40°F - 200°F

\*Information on this data sheet is subject to change without notice and should not be used for writing specifications.

For additional information on specific applications, contact Accumetric, LLC



### DESCRIPTION

BOSS<sup>®</sup> 125 Multi-Seal Building/Construction Sealant is a multi-purpose, one part sealant, formulated from a hybrid polymer. This unique sealant is free from solvents, silicone, isocyanates and other hazardous raw materials. It cures on exposure to atmospheric moisture to form a highly durable flexible sealant.

Multi-Seal has been formulated to offer outstanding primerless adhesion to most common building materials including vinyl, aluminum, steel, concrete, wood and glass. It can be applied and tooled under most weather conditions. This sealant is paintable with most latex base paints\*.

\*Test small area for compatibility before painting

### FEATURES

- VOC Compliant in all 50 states
- Ease of use, one-part sealant, no mixing required
- Good weatherability - virtually unaffected by sunlight, rain, snow, ozone, and temperature extremes
- Good UV resistance and color stability
- Long life reliability; cured sealant stays flexible without tearing, cracking, drying out, or becoming brittle.
- With its non slump properties, can be used in vertical, horizontal and overhead joints
- Wide temperature gunnability; can be applied in any season
- Non-yellowing and non-staining
- Non-streaking
- Paintable with most latex base paints\*
- Free from solvents and isocyanates

## LIMITATIONS

- Do not use for structural glazing

## APPLICATIONS

**BOSS® 125** Multi-Seal Building/Construction Sealant is designed to produce a flexible joint sealant with excellent adhesion to various substrates. **BOSS® 125** is suited to sealing construction joints in concrete structures, masonry joints, balcony and parapet joints, window and door perimeter joints, facade and metal cladding joints, ceramic tilt joints, shop fronts, aluminum angle joints, showcases and shower screens.

**BOSS® 125** Multi-Seal Building/Construction Sealant has excellent adhesion to many types of vinyl, fiberglass, ABS plastic, nylon 6/6, polycarbonate, PVC, porcelain tiles and glass and can be used around these substrates.

## SPECIFICATIONS

**BOSS® 125** meets TT-S-000230C, Type II, Class A; ASTM C920, Type S, Grade NS, Class 25, Use NT, G, M, A and O; CAN/CGSB 19.13-M87.

## HOW TO USE

**Make sure the joint design is correct.** Proper joint design minimizes stresses on the sealant. Typical dimensions of a movement joint should ensure the width of the joint would equal two times the depth of sealant. Minimum depth of sealant in construction joint should be 6mm.

**Clean the joint surface on both new and old jobs.** Surfaces must be clean, dry, and sound. Since new material is often covered with a protective film, solvent-wash all surface materials with a wet brush and an oil-free solvent. Ensure that surfaces are dust free.

**Use masking tape where bead lines of exact shapes are required.** Masking tape should be removed immediately after a bead is completed before a skin begins to form.

**Apply sealant to dry, clean surfaces.** An air-operated or hand-operated cartridge or sausage gun may be used. Surfaces should be dry before the sealant is applied.

Ensure that surfaces to receive the sealant are dust free. Uncured sealant may be cleaned from tools using commercial solvent.

**Tool joint, if necessary, and remove masking tape.** Tooling should be completed in one continuous stroke. Tool immediately after sealant is applied and before a skin begins to form. Do not use soap or oil as a tool aid. Remove masking tape immediately after tooling is completed.

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **BOSS® 125** Multi-Seal Building/Construction Sealant has a shelf life of 12 months from date of shipment. In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

## COLORS

**BOSS® 125** Multi-Seal Building/Construction Sealant is available in grey, white and black.

## CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use with adequate ventilation. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN.

## PACKAGING

**BOSS® 125** is available in standard caulking cartridges.

## SHIPPING LIMITATIONS

None.

Reactive VOC 15 g/l (<1% wt)

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.

MADE IN U.S.A.

## BOSS® PRODUCTS

Accumetric, LLC  
350 Ring Road  
Elizabethtown,  
Kentucky 42701 USA  
800-928-BOSS(2677)  
TEL (270)769-3385  
FAX (270)765-2412  
Outside U.S.  
TEL +1(270)769-3385  
FAX +1(270)765-2412

Accumetric Asia Pacific, LTD  
18 Kitpanit Bldg. 5th Floor  
#502 Patpong Road  
Suriyawong, Bangrak  
Bangkok, 10500 Thailand  
TEL (662)634-3060  
FAX (662)634-3066

[www.bossproducts.com](http://www.bossproducts.com)